

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : A61B 19/04, C08L 13/02	A1	(11) International Publication Number: WO 00/21451 (43) International Publication Date: 20 April 2000 (20.04.00)
<p>(21) International Application Number: PCT/GB99/03470</p> <p>(22) International Filing Date: 13 October 1999 (13.10.99)</p> <p>(30) Priority Data: 9822358.9 13 October 1998 (13.10.98) GB</p> <p>(71) Applicant (<i>for all designated States except US</i>): LRC PRODUCTS LIMITED [GB/GB]; Turnford Place, Broxbourne, Hertfordshire EN10 6LN (GB).</p> <p>(72) Inventors; and (75) Inventors/Applicants (<i>for US only</i>): TEOH, Seng, Chin [MY/MY]; 92 Taman Jesselton, 10450 Penang (MY). CHEN, Seong, Fong [MY/MY]; 11a Gerbang Minden, Gelugor, 11700 Penang (MY).</p> <p>(74) Agents: WAIN, Christopher, Paul et al.; A.A. Thornton & Co., 235 High Holborn, London WC1V 7LE (GB).</p>	<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>	
<p>(54) Title: ELASTOMERIC GLOVES</p> <p>(57) Abstract</p> <p>An elastomeric carboxylated nitrile rubber glove has a stress retention, after six minutes at 100 % extension, of from 50 % to 70 %. It is made using prevulcanised carboxylated nitrile rubber latex with 2 to 6 % by weight methacrylic acid equivalent.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

- 1 -

ELASTOMERIC GLOVES

This invention relates to elastomeric gloves, particularly but not exclusively medical and surgical gloves, and to a method of making them.

Close fitting rubber gloves are well known and are used for a number of purposes, principally medical and surgical. It is especially important in some uses for the gloves to fit closely on the hand, at least in the finger and palm regions. To ensure this close fitting, it is customary for users to wear gloves of slightly smaller dimensions than their hands in order to ensure a close snug fit. However, some discomfort can arise during use of the gloves, from the continued application of pressure by the glove on the hand.

It has been proposed in EP-B-0456333 to overcome this problem by making such gloves of nitrile butadiene rubber since this material has long been known to show stress relaxation properties. In particular, the patent describes gloves made of a carboxylated elastomeric material comprising 0.1 to 0.5 parts zinc oxide per 100 parts carboxylated nitrile butadiene rubber, the material being such that when stretched 100% of its length with an initial stress and the 100% stretch maintained, the material relaxes within 6 minutes of the initial stress so that the 100% stretch is maintained by a reduced stress which is less than 80%, more preferably less than 50%, of the initial stress. The effect of this is that whilst the gloves are tight fitting when initially donned, the stress subsequently relaxes within six minutes so as to relieve the pressure applied to the user's hands and so

- 2 -

provide greater comfort and sensitivity. In the only Example in the patent, the stress retention of a carboxylated nitrile butadiene rubber glove was 0% after six minutes.

Whilst this basic approach of using the known stress relaxation properties of carboxylated nitrile rubbers does provide some alleviation of the problem of user discomfort due to stress retention in rubber gloves, it does not provide a wholly satisfactory answer. In particular, we have found that the stress retention which occurs in known carboxylated nitrile rubbers such as taught by EP-B-0456333 is actually too low such that its use can result in poor fitting of gloves to the hands and fingers as the gloves gradually become loose with time because of creep due to stress relaxation. In particular, we have found that stress retention of less than 50% as is found in known such rubbers, can give rise to problems and that, surprisingly, far improved user comfort and satisfaction is achieved with a stress retention of from about 50 to about 70%.

Accordingly, in one aspect, the present invention provides an elastomeric glove made of a carboxylated nitrile rubber having from 2 to 6% by weight methacrylic acid equivalent and which exhibits a stress retention of from 50 to 70%, said stress retention being the percentage retention of the initial stress after six minutes at 100% extension. Gloves of the invention give better fitting to the hands and fingers and hence improved sensitivity of touch on extended wearing compared with those that have low stress retention of less than 50%.

The stress retention of the gloves produced according to the present invention is higher than that illustrated and obtained by EP-B-0456333, but lower than that of gloves made from natural rubber latex or polychloroprene latex. The gloves of the invention can be made to be good fitting and yet not to cause fatigue to the hands on extended wearing.

Gloves made of conventional carboxylated nitrile rubbers have a low stress retention, i.e. well below 50%. Accordingly, gloves of the present invention cannot be made by simply using known nitrile rubber glove technology since the

stress retention would then be too low. We have found, however, that stress retention can be controllably increased to the levels required in the present invention by using prevulcanised nitrile butadiene rubber latex, i.e. latex in which some vulcanisation of the rubber by sulphur has been effected before the gloves are made. Pre-vulcanisation (or maturation) of the rubber in this way then enables the desired stress retention of 50 to 70% to be obtained following a conventional dipping production process.

The gloves of the invention can be non-chlorinated or chlorinated or polymer-coated, as desired. The carboxylated nitrile rubber latex used to make the gloves is preferably a copolymer of acrylonitrile, butadiene, and an unsaturated carboxylic acid. The unsaturated carboxylic acid is of acrylic acid type and may be, for example, acrylic acid, methacrylic acid, crotonic acid, itaconic acid, fumaric acid, or sorbic acid. Methacrylic acid is preferred. The ratio of acrylonitrile to butadiene in the copolymer will depend upon the use to which the glove is to be put. For an industrial glove requiring good resistance to organic solvents, the acrylonitrile content may be as high as 37 to 40% of the polymer. For surgical and other medical gloves, solvent resistance is much less important than softness and flexibility. In this case, a copolymer of much lower acrylonitrile content is used, usually about 26 to 30% of the polymer. The preferred amount of unsaturated carboxylic acid is 2 - 6% methacrylic acid equivalent, most preferably 3 - 5.5% methacrylic acid equivalent.

In the gloves of the invention, the nitrile rubber is cross-linked both by conventional vulcanisation (i.e. by sulphur, vulcanisation accelerators and zinc oxide), and by ionic crosslinking using polyvalent metal oxides, preferably zinc oxide. The amount of polyvalent metal oxide (eg. zinc oxide) used for the ionic cross-linking is preferably from about 0.1 to 0.5 phr (per hundred parts of nitrile rubber, dry basis), more preferably from 0.2 to 0.4 phr. The polyvalent metal oxides effect crosslinking ionically between carboxylate groups in the polymer chain. The amount of sulphur used for crosslinking is from 1 to 3 phr, preferably

from 2 to 3 phr. The crosslinking of the nitrile polymers achieved by sulphur crosslinks (both during the process and during prevulcanisation) is the major effect and the ionic crosslinking via the polyvalent metal oxide and the carboxyl groups is the minor effect. The selection of a low level of carboxylation and of a low polyvalent metal oxide level keep the level of ionic crosslinks in the nitrile rubber relatively low. Ionic crosslinks exhibit higher stress relaxation characteristics than do sulphur crosslinks. The stress retention achieved can be controlled by varying the amounts of, and balance between, the two types of crosslink.

According to the invention, the carboxylated nitrile rubber latex is subjected to a prevulcanisation (or maturation) step. Preferably, this is at least at 30°C for a minimum of 16 hours for fully compounded latex. As will be clear to those skilled in the art, however, different temperatures and times can be used to provide essentially the same effect and the invention encompasses these equivalents. In general, lower temperatures will require longer times, and higher temperatures shorter times. The practical minima and maxima will be readily determinable by those skilled in the art with any particular latex formulation, bearing in mind the ultimate purpose of providing gloves with a stress retention of from 50 to 70%.

In order that the invention may be more fully understood, the following Examples are given by way of illustration only.

Carboxylated acrylonitrile butadiene latices with a carboxylation level of 4% - 6% methacrylic acid equivalent content were compounded according to Formulation A given in Table 1. Formulation B given in Table 2 has also been used. The latex was prevulcanised at 40°C for various periods of time. Prevulcanisation at 50°C has also been used. After the required heating time, the latex was cooled. Gloves were prepared from the prevulcanised latex by well-known procedures, involving the steps of coagulant dipping, leaching, drying, and vulcanising. The gloves were then finished, either by washing and powdering, or

- 5 -

by washing and chlorination, as indicated in the Examples that follow.

The gloves were tested according to ASTM methods.

In the following Examples, carboxylated acrylonitrile butadiene rubber is referred to as XNBR, zinc dibutyl dithiocarbamate as ZBuD, zinc mercaptobenzthiazole as ZMBT and zinc diethyl dithiocarbamate as ZDEC.

Examples 1 - 3 illustrate that conventional nitrile rubber formulations containing zinc oxide levels above 1 phr produce gloves with stress retention less than 50%.

Example 1

Carboxylation level of nitrile polymer in latex = ca. 6% methacrylic acid

<u>Formulation</u>	<u>phr</u>	
XNBR	100	
S	2.0	
ZBuD		1.0
ZMBT	0.5	
ZnO	2.0	

Latex maturation at ambient temperature, 30°C ± 4°C for 24 hours.

Stress retention of gloves produced = 45%

Example 2

Carboxylation level of nitrile polymer in latex = ca. 6% methacrylic acid

<u>Formulation</u>	<u>phr</u>
XNBR	100
S	1.0
ZBuD	0.25
ZnO	2.8

- 6 -

Latex maturation at ambient temperature, $30^{\circ}\text{C} \pm 4^{\circ}\text{C}$ for 6 days.

Stress retention of gloves produced = 38%

Example 3

Carboxylation level of nitrile polymer latex = ca. 4% methacrylic acid

<u>Formulation</u>	<u>phr</u>
XNBR	100
ZDEC	0.5
ZMBT	0.5
ZnO	4.0
S	1.0

Latex maturation at ambient temperature, $30^{\circ}\text{C} \pm 4^{\circ}\text{C}$ for 4 days.

Stress retention of gloves produced = 42%

Example 4

This Example illustrates that ionic crosslinks using a formulation containing zinc oxide only (no sulphur vulcanisation occurs) produces gloves with low stress retention of about 30%.

Carboxylation level of nitrile polymer in latex = ca. 4% methacrylic acid

<u>Formulation</u>	<u>phr</u>
XNBR	100
ZnO	1.5

Latex prevulcanisation at 40°C for 48 hours, 72 hours, 96 hours and 168 hours.

Stress retention of gloves produced in all cases = $30 \pm 2\%$

- 7 -

Examples 5 - 8 illustrate the use of Formulation A to produce gloves with stress retention >50%. Physical properties of the gloves are also given.

Example 5

Carboxylation level of nitrile polymer in latex = ca. 4% methacrylic acid

<u>Formulation</u>	<u>phr</u>
XNBR	100
S	2.0
ZDEC	0.75
ZnO	0.25

Latex prevulcanisation at 40°C for 48 hours - 96 hours.

Time, hr	Stress retention %		Tensile strength, MPa		M500 MPa		EB,%	
	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>
48	62 ± 2	62 ± 2	17.7	16.6	5.5	5.3	660	660
72	66 ± 2	63 ± 3	18.5	15.0	6.0	5.7	640	630
96	63 ± 3	61 ± 3	19.4	17.4	7.5	6.6	615	635

ncl - non-chlorinated gloves

cl - chlorinated gloves

Example 6

This Example illustrates that by reducing the ZDEC level in Example 5, gloves with lower modulus, M500, are produced.

Carboxylation level of nitrile polymer in latex = ca. 4% methacrylic acid

- 8 -

<u>Formulation</u>	<u>phr</u>
XNBR	100
S	2.0
ZDEC	0.50
ZnO	0.25

Latex prevulcanisation at 40°C for 48 hours - 96 hours

Time, hr	Stress retention %		Tensile strength, MPa		M500, MPa		EB, %	
	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>
48	56 ± 2	54 ± 3	16.1	17.7	4.3	4.1	710	735
72	62 ± 4	57 ± 2	15.9	16.1	4.1	4.1	715	725
96	60 ± 2	56 ± 2	16.0	19.8	4.1	4.9	720	725

Example 7

Carboxylation level of nitrile polymer in latex = ca. 5.5% methacrylic acid

<u>Formulation</u>	<u>phr</u>
XNBR	100
S	2.0
ZDEC	0.75
ZnO	0.30

Latex prevulcanisation at 40°C for 48, 72, 96 and 168 hours.

- 9 -

Time, hr	Stress retention %		Tensile strength, MPa		M500, MPa		EB,%	
	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>
48	55 ± 1	55 ± 2	21.4	26.8	4.6	5.9	690	685
72	---	---	25.8	28.3	4.9	5.9	690	685
96	59 ± 3	59 ± 1	28.8	26.6	6.4	5.4	660	690
168	65 ± 2	59 ± 2	25.0	23.9	5.7	4.8	670	690

Example 8

This Example illustrates that when the carboxylation level of the nitrile latex is high at 6% methacrylic acid content, the stress retention of the gloves produced is reduced compared with Examples 5 - 7.

Carboxylation level of nitrile polymer in latex = ca. 6% methacrylic acid

<u>Formulation</u>	<u>phr</u>
XNBR	100
S	2.0
ZDEC	0.75
ZnO	0.30

Latex prevulcanisation at 40°C for 48 hours - 168 hours

Time, hr	Stress retention %		Tensile strength, MPa		M500, MPa		EB,%	
	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>	<u>ncl</u>	<u>cl</u>
48	53 ± 1	49 ± 3	37.7	49.0	11.8	24.7	610	560
72	50 ± 1	52 ± 2	36.8	37.2	7.8	9.0	680	670
168	52 ± 3	51 ± 1	21.6	19.0	2.2	2.7	715	695

- 10 -

Example 9

This Example illustrates the use of Formulation B to produce gloves with stress retention >50%.

Carboxylation level of nitrile polymer in latex = ca. 4% methacrylic acid

<u>Formulation</u>	<u>phr</u>
XNBR	100
S	2.0
ZDEC	0.35
ZMBT	0.35
DPG	0.65
ZnO	0.20

Latex prevulcanisation at 40°C for 48, 72 hours and 96 hours

Time, hr	Stress retention %		Tensile strength, MPa		M500, MPa		EB,%	
	<u>ncI</u>	<u>cl</u>	<u>ncI</u>	<u>cl</u>	<u>ncI</u>	<u>cl</u>	<u>ncI</u>	<u>cl</u>
48	57 ± 1	58 ± 1	20.4	20.3	7.9	8.0	610	615
72	59 ± 1	56 ± 1	18.9	19.6	6.1	5.7	650	660
96	62 ± 3	57 ± 3	19.7	22.4	6.5	6.6	650	655

The difference between formulation A and formulation B is in the accelerators used. A general formulation is shown in Table 3.

- 11 -

Table 1: Nitrile Latex Formulation A

	phr
XNBR	100.0
Potassium hydroxide	0 - 0.5
Sodium dodecyl benzene sulphonate	0.1 - 0.5
Ammonia solution	to adjust pH to ca. 9.5
Sulphur	1 - 3
Zinc diethyl dithiocarbamate	0.2 - 1.0
Zinc oxide	0.1 - 0.5
Wingstay L	0 - 1.0
Titanium dioxide	2.0 - 5.0
Coagulant WS	0 - 2.0
Water	to dilute latex to 30% - 35% total solids content
Pigment	0 - 0.5

Table 2: Nitrile Latex Formulation B

	phr
XNBR	100.0
Potassium hydroxide	0 - 0.5
Sodium dodecyl benzene sulphonate	0.1 - 0.5
Ammonia solution	to adjust pH to ca. 9.5
Sulphur	1 - 3
Zinc diethyl dithiocarbamate	0.20 - 1.0
Zinc mercaptobenzthiazole	0.2 - 0.5
Diphenyl guanidine	0.4 - 0.8
Zinc oxide	0.1 - 0.5
Wingstay L	0 - 1.0
Titanium dioxide	2.0 - 5.0
Coagulant WS	0 - 2.0
Water	to dilute latex to 30% - 35% total solids content
Pigment	0 - 0.5

- 12 -

Table 3 General Nitrile Formulation

	phr
XNBR	100.0
Potassium hydroxide	0 - 0.5
Sodium dodecyl benzene sulphonate	0.1 - 0.5
Ammonia solution	to adjust pH to ca. 9.5
Sulphur	1 - 3
Vulcanisation accelerator(s)	0.2 - 2.5
Zinc oxide	0.1 - 0.5
Wingstay L	0 - 1.0
Titanium dioxide	2.0 - 5.0
Coagulant WS	0 - 2.0
Water	to dilute latex to 30% - 35% total solids content
Pigment	0 - 0.5

- 13 -

CLAIMS:

1. An elastomeric glove made of a carboxylated nitrile rubber having from 2 to 6% by weight methacrylic acid equivalent and which exhibits a stress retention of from 50 to 70%, said stress retention being the percentage retention of the initial stress after six minutes at 100% extension.
2. A glove according to claim 1, which contains from 3 to 5.5% by weight methacrylic acid equivalent.
3. A glove according to claim 1 or 2, in which the carboxylated nitrile rubber has been cross-linked with from 1 to 3 phr sulphur and less than 0.5 phr polyvalent metal oxide.
4. A glove according to claim 3, wherein from 0.5 - 1.5 phr vulcanisation accelerator is used.
5. A glove according to claim 3 or 4, wherein the polyvalent metal oxide is zinc oxide.
6. A glove according to any preceding claim, wherein the carboxylated nitrile rubber is a copolymer of acrylonitrile, butadiene and an unsaturated carboxylic acid.
7. A glove according to claim 6, wherein the unsaturated carboxylic acid is of acrylic acid type.
8. A glove according to claim 7, wherein the carboxylic acid is acrylic acid, methacrylic acid, crotonic acid, itaconic acid, fumaric acid or sorbic acid.

- 14 -

9. A glove according to any preceding claim, which contains up to about 40% nitrile content and is an industrial solvent-resistant glove.
10. A glove according to any of claims 1 to 8, which contains up to about 30% nitrile content and is a surgical or medical glove.
11. A glove according to any preceding claim which exhibits a stress retention of from 55 to 70%.
12. A method of making a carboxylated nitrile rubber glove having a stress retention of from about 50% to about 70%, said stress retention being the percentage retention of the initial stress after six minutes at 100% extension, which method comprises dipping a former into a pre-vulcanised carboxylated nitrile rubber latex formulation, the rubber having from 2 to 6% methacrylic acid equivalent, the latex formulation containing from 1 to 3 phr sulphur, from 0.5 to 1.5 phr vulcanisation accelerator, and less than 0.5 phr polyvalent metal oxide.
13. A method according to claim 12, wherein the rubber latex has been prevulcanised by storage of the formulation at 30°C for at least 16 hours, or the equivalent.
14. A method according to claim 12 or 13, wherein the formulation contains from 2 to 3 phr sulphur and from 0.1 to less than 0.5 phr zinc oxide.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 99/03470

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61B19/04 C08L13/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08L A61B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 456 333 A (TILLOTSON CORP) 13 November 1991 (1991-11-13) cited in the application abstract; claims; example ---	1-14
X	WO 97 48765 A (SIEBE NORTH INC) 24 December 1997 (1997-12-24) abstract; claims; example page 5, line 2 - line 17 ---	1-14
X	DE 196 18 006 A (BASF AG) 6 November 1997 (1997-11-06) abstract; claims; examples page 3, line 14 - line 21 ---	1-14
X	EP 0 559 150 A (NIPPON ZEON CO) 8 September 1993 (1993-09-08) abstract; claims; example 12; table 1 ---	1-14
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

17 January 2000

Date of mailing of the international search report

24/01/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Mettler, R-M

INTERNATIONAL SEARCH REPORT

Inter. Patent Application No

PCT/GB 99/03470

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	<p>WO 99 06481 A (KRISHNAN VENKATARAM ;REICHHOLD CHEMICALS INC (US); GHOSAL KANCHAN) 11 February 1999 (1999-02-11) abstract; claims; example 3 -----</p>	1-14

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 99/03470

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0456333 A	13-11-1991	US 5014362 A	14-05-1991
		AT 166091 T	15-05-1998
		DE 69129381 D	18-06-1998
		DE 69129381 T	29-10-1998
		ES 2119759 T	16-10-1998
		US RE35616 E	30-09-1997
WO 9748765 A	24-12-1997	AU 3572097 A	07-01-1998
		EP 0925329 A	30-06-1999
DE 19618006 A	06-11-1997	AU 2769997 A	26-11-1997
		CN 1211210 A	17-03-1999
		WO 9742017 A	13-11-1997
		EP 0904184 A	31-03-1999
		NO 985119 A	03-11-1998
EP 0559150 A	08-09-1993	JP 2692483 B	17-12-1997
		JP 5247266 A	24-09-1993
		JP 6182788 A	05-07-1994
		DE 69315868 D	05-02-1998
		DE 69315868 T	16-04-1998
		US 5369166 A	29-11-1994
WO 9906481 A	11-02-1999	US 5910533 A	08-06-1999
		AU 8681298 A	22-02-1999